

**Amendments to the Specification**

Pursuant to 37 CFR 1.121(b)(iii), please substitute the following for the first paragraph on page 15 of the specification.

|  | Polymer                  |  | Example |      |  |  |
|--|--------------------------|--|---------|------|--|--|
|  |                          |  | 1       | 2    |  |  |
|  | Appear™ 3000-B           |  | 10      |      |  |  |
|  | AryLite™ A100            |  |         | 10   |  |  |
|  | Ruthenium dioxide powder |  | 21.6    | 21.6 |  |  |
|  | Bismuth ruthenate powder |  | 15.7    | 15.7 |  |  |
|  | Silver powder            |  | 5.0     | 5.0  |  |  |
|  | Alumina                  |  | 4.5     | 4.5  |  |  |
|  | Dowanol® PPH             |  | 56      |      |  |  |
|  | BLO                      |  |         | 56   |  |  |

  

| Example | Tg   | % H <sub>2</sub> O | % Resistance Change       |              |              |             |
|---------|------|--------------------|---------------------------|--------------|--------------|-------------|
|         | (°C) | Absorption         | Solder Float (3 x 10 sec) |              |              | 85°C/85% RH |
|         |      |                    | <u>230°C</u>              | <u>260°C</u> | <u>288°C</u> | (500 hrs)   |
| 1       | 330  | 0.03               | -0.9                      | 28.4         | 205          | +1.8        |
| 2       | 325  | 0.4                | -1.5                      | 32.9         | --           | -3.4        |